

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
7 April 2005 (07.04.2005)

PCT

(10) International Publication Number  
WO 2005/030818 A2

(51) International Patent Classification<sup>7</sup>: C08F 110/02,  
4/70, 200

(21) International Application Number:  
PCT/EP2004/052291

(22) International Filing Date:  
23 September 2004 (23.09.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
03 11391 29 September 2003 (29.09.2003) FR

(71) Applicants (for all designated States except US): TOTAL PETROCHEMICALS RESEARCH FELUY [BE/BE]; Zone Industrielle C, B-7181 Seneffe (Feluy) (BE). CENTRE NATIONAL DE LA RECHERCHE SCIENTIFIQUE [FR/FR]; 3, Rue Michel Ange, F-75016 Paris (FR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): LAVASTRE, Olivier [FR/FR]; La Mazure, F-35490 Gahard (FR). GALLARD, Laurent [FR/FR]; L'Isle, 11, Rue des Pêcheurs, F-79170 Villiers sur Chizé (FR). RAZAVI,

Abbas [IR/BE]; 35, Domaine de la Brisée, B-7000 Mons (BE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIP0 (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



A2

(54) Title: BIMODAL POLYETHYLENE

(57) Abstract: The present invention discloses a method for preparing a catalyst component suitable for the preparation of bimodal polymers that comprises the steps of: a) providing hollow beads of polyethylene of controlled morphology and size; b) drying the hollow beads under vacuum; c) impregnating the dried hollow beads with a concentrated solution of the desired catalyst component under vacuum; d) submitting the impregnated hollow beads to atmospheric pressure; e) draining excess liquid; f) drying under inert gas at atmospheric pressure. It also discloses a method for preparing bimodal polymers that uses the new catalyst component catalyst.

WO 2005/030818 A2